

Electrocoating of Titanium Nanoparticle and Investigation of its Characters

Soodabeh Rafieinasab¹, Jamal Sedaghatnia

Electrochemistry Research Laboratory, Islamic Azad University Abarkooh Branch, Iran

Received: 09 December 2019

Accepted: 22 January 2020

Published: 01 March 2020

Abstract

Titanium oxide nanotubes were fabricated by anodic oxidation of a pure titanium sheet in 1.5 M H₂SO₄, 0.3 M H₃PO₄ and 0.3 M H₂O₂ mixture solution. The morphology of Titanium oxide nanotubes surface were investigated by scanning electron microscope (SEM). These tubes are well aligned and organized into high-density uniform arrays. While the tops of the tubes are open, the bottoms of the tubes are closed, forming a barrier layer structure similar to that of porous alumina. The average tube diameter, ranging in size from 40 to 70 nm.

Keywords: Nanotubes; Titanium Oxide; Anodizing; Scanning Electron Microscope.

How to cite the article:

S. Rafieinasab, J. Sedaghatnia, *Electrocoating of Titanium Nanoparticle and Investigation of its Characters*, *Medbiotech J.* 2019; 4(1): 019-021, DOI: 10.22034/mbt.2020.105878.

©2020 The Authors. This is an open access article under the CC BY license

1. Introduction

Titanium and its alloys are increasingly used in technological applications due to their excellent mechanical properties, high corrosion resistance and good biocompatibility [1-3]. Furthermore oxide layers on Ti and particularly TiO₂ also have attracted much attention because TiO₂ possesses a variety of functional properties as for example for gas sensing [4], self-cleaning [5], solar energy conversion [6], wettability [7] and photocatalysis [8] applications. In recent years, the formation of self-organized pores has been achieved on various valve metals Al [9], Zr [10], Hf [11], Nb [12], Ta [13] and W [14] including Ti. In this work, we examine the morphology of porous titanium oxide thin films fabricated by anodizing pure titanium sheets under variable conditions. It has been found that the anodized titanium films have more complicated morphologies than anodized aluminum. In addition to porous films, such as those reported earlier well-aligned nanotubelike structures composed of

titanium oxide were obtained. In contrast to the continuous pore structures achieved with aluminum anodization, discrete titanium oxide nanotubes are found to grow from the discontinuous nanoporous titanium oxide film.

2. Experimental

Pure titanium plates (purity %99.99, 25×10×1mm) were used. The chemical composition of samples has been given in table 1. The titanium specimens were mechanically polished and degreased in acetone for 5 min and then washed and dried. After the pre-treatment, Anodizing of titanium carried out with two methods:

Titanium Samples anodized in 0.5 wt% HF solution at a constant voltage of 20 V.

a) Titanium Samples anodized in 1.5M H₂SO₄+ 0.3M H₃PO₄+ 0.3M H₂O₂ mixture solution at a constant voltage of 70 V. The morphologies of the titanium oxide films were characterized with a Philips (Tokyo, Japan) scanning electron microscope (SEM).

¹ Corresponding author email: s_m_rafieian22@yahoo.com

Table 1. The chemical composition of Titanium used in this work

Element	Fe	O	Cu	Ni	C	Ti
Wt. %	0.17	0.29	0.07	0.09	0.04	rest

3. Results and discussion

In anodizing process, titanium plates is immersed into an electrolyte and connected as an anode, leading to the formation of an oxide film at the surface. In moderately alkaline, neutral and moderately acidic aqueous solutions, TiO₂ is the only thermodynamically stable titanium compound, according to the Pourbaix diagram [15]. The corrosion potential of naked metallic titanium is more negative than that of water reduction, and thus rapid corrosion starts immediately upon immersion of titanium into any aqueous solution [16], according to the equation $Ti + 2H_2O = TiO_2 + 2H_2$. TiO₂ layers are known to be very compact, poorly conducting, and only little permeable for water and gases, and furthermore the reversible potential of the oxidized surface (Ti/TiO₂ electrode) becomes more positive in comparison to the potential of the naked metal. Consequently, the corrosion of titanium is a self-inhibiting process. The TiO₂ layer is highly resistive and the oxidation reaction will stop when the applied voltage is equal to the ohmic drop in the oxide film. Figure 1 shows current transient curves recorded during anodization in 0.5 wt% HF solution at a constant voltage of 20 V. For comparison the behavior in 1.5M H₂SO₄+0.3M H₃PO₄+0.3M H₂O₂ mixture solution at a constant voltage of 70 V is included. In the 0.5 wt% HF containing electrolyte a clear deviation from the behavior in the 1.5M H₂SO₄+0.3M H₃PO₄+0.3M H₂O₂ mixture electrolyte can be observed, that is, on the one hand that the current drops more slowly in the initial phase and on the other hand the current rises again after the initial decay. After extended polarization the current density in HF containing electrolyte is higher than the steady-state in 1.5M H₂SO₄+0.3M H₃PO₄+0.3M H₂O₂ mixture electrolyte, which indicates that an additional dissolution process takes place in the presence of fluorides. This finding can be ascribed to the dissolution of the electrochemically formed TiO₂ as soluble hexafluorotitanium complexes [TiF₆]⁻², which go into solution. The curve shape, showing a decrease/increase/decrease sequence, has been reported on Al and Ti, and may be assigned to different stages during a self-ordering process [17]. In 1.5M H₂SO₄+0.3M H₃PO₄+0.3M H₂O₂ mixture electrolyte, on the other hand, extended anodization resulted in a steady-state value that represents a leakage through a compact oxide layer. After anodization in this electrolyte no porous structures could be

observed – just a compact oxide layer was present on the surface.




Figure 1. Current transient curves during electrochemical anodization in 0.5 wt% HF solution (solid line) and in 1.5M H₂SO₄+0.3M H₃PO₄+0.3M H₂O₂ mixture solution (dashed line).

SEM permits observation of specimens with large magnification and great depth of field by means of detection of secondary electrons. The number of secondary electrons depends on several factors, the most important being the angle between the primary electron beam and the local surface of the observed specimen. Figure 2(a) shows a typical scanning electron microscope (SEM) micrograph of the porous structures obtained under anodizing voltage 70 V, in 1.5 M H₂SO₄, 0.3 M H₃PO₄ and 0.3 M H₂O₂ mixture. The morphology of the porous film is similar to that of porous (sponge like) alumina, with a typical pore size of 40 to 70 nm. It can be seen that Titanium oxide nanotubes exhibits uniform tube morphology, the tubes open on the top and close at the bottom, nearly parallel and closed side by side. Figure 2(b) shows a SEM image of the porous structures obtained under anodizing voltage 20 V, in 0.5 wt% HF solution. It is clear that the anodic TiO₂ layer was less porous than that of anodic film formed in 1.5M H₂SO₄+0.3M H₃PO₄+0.3M H₂O₂ mixture. The SEM images show that the Surface morphologies of anodic TiO₂ films, depends on electrolyte composition and working conditions in anodizing.

4. Conclusions

Well-aligned titanium oxide nanotubelike arrays have been obtained through titanium anodization in 1.5M H₂SO₄+ 0.3M H₃PO₄+ 0.3M H₂O₂ mixture solution at a constant voltage of 70 V. The resulting nanotubes are straight, with a pore size ranging from 40 to 70 nm, and have a barrier layer at their bottom. The SEM images show that the Surface morphologies of anodic TiO₂ films, depends on electrolyte composition and working conditions in anodizing.




Figure 2. Surface morphologies of (a) Titanium sheet anodized under voltage of 70 V in 1.5 M H₂SO₄ + 0.3 M H₃PO₄ + 0.3 M H₂O₂ mixture solution (b) Titanium sheet anodized under voltage of 20 V in 0.5 wt% HF solution.

References

- Narmin Najafzadeh MMS, Syed Shuja Sultan, Adel Spotin, Alireza Zamani, Roozbeh Taslimian, Amir Yaghoubinezhad, Parviz Parvizi. The existence of only one haplotype of *Leishmania major* in the main and potential reservoir hosts of zoonotic cutaneous leishmaniasis using different molecular markers in a focal area in Iran. *Revista da Sociedade Brasileira de Medicina Tropical*. 2014;47(5).
- Aye Rizvandi MTG, Mohammadreza Esmaeili, Farideh Ashraf Ganjooe. The Evaluation of Performance Indicators of Coaches in Football Development. *Journal of Humanities Insights*. 2019;3(4).
- Somayyeh Heidary AYN, Atefeh Mehrabi Far. Colonization and Investigation of *Vibrio Cholera* Recombination Protein in E-Coli. *International Journal of Engineering & Technology*. 2018;7(4.7).
- S. Mojtaba Mostafavi BR. *Nanomaterial Chemistry*. Toranj Group Publication, Ltd.; 2010.
- Rizvandi A, Taghipour Gharbi M, Esmaeili M, Ashraf Ganjooe F. The Evaluation of Performance Indicators of Coaches in Football Development. *Journal of Humanities Insights*. 2019;03(04):248-54.
- Neda Samei PP, Mohammadreza Khatami Nezhad, Amir Yaghoubinezhad, Narmin Najafzadeh, Adel Spotin. Finding various molecular haplotypes of *Leishmania major* in human using three HSp70, ITS-rDNA and Cyt b genes. 1st and 13th Iranian Genetics Congress; Tehran 2014.

- Neda Samei PP, Adel Spotin, Mohammad Reza Khatami Nezhad, Narmin Najafzadeh, Amir Yaghoubinezhad. IDENTIFYING OF CAUSATIVE AGENTS OF CUTANEOUS LEISHMANIASIS BY AMPLIFYING CYT B GENE IN INDIGENOUS FOCI OF Iran. *Iranian Journal of Public Health*. 2014;43(2).
- Adel Spotin SR, Parviz Parvizi, Parnazsadat Ghaemmaghami, Ali Haghghi, Aref Amirkhani, Ali Bordbar, Amir Yaghoubinezhad. Different Phenotypic Aspects with No Genotypic Heterogeneity in *Leishmania Major* Isolates of Suspected Patients in Northern Khuzestan Province. *Iranian Journal of Public Health*. 2014;43(2).
- Nezhad AY, SH AMF, Piryaei M, Mostafavi SM. Investigation of *Shigella* lipopolysaccharides effects on immunity stimulation of host cells. *International Transaction Journal of Engineering, Management, Applied Sciences and Technologies*. 2019;10:465.
- Mehdi Kargarfard RR, Aye Rizvandi, Mehdi Dahghani, Parinaz Poursafa. Hemodynamic physiological response to acute exposure to air pollution in young adults according to the fitness level. *ARYA Atherosclerosis*. 2009;5(3).
- Aye Rizvandi FT. Entrepreneurial marketing effects on sport club manager performance (Conceptual Model). *Universidad de Alicante Área de Educación Física y Deporte*. 2019;14.
- Aye Rizvandi FT, Zaheh Sadegh Zadeh. Sport consumer behaviour model: Motivators and constraints. *Universidad de Alicante Área de Educación Física y Deporte*. 2019;14.
- Mostafavi SM, Pashae F, Rouhollahi A, Adibi M, editors. *Electrochemical Study and Determination of Thiophene by Cobalt Oxide Nanoparticle Modified Glassy Carbon Electrode*. 6th Aegean Analytical Chemistry Days (AACD), Denizli, Turkey; 2008.
- Aye Rizvandi MF, Maryam Asadollahi Supply Chain Management for Sporting Goods Retailing: Mikima Book Publication; 2020.
- Seyed Mojtaba Mostafavi MP, Ahmad Rouhollahi, Mohajeri A. Separation and Quantification of Hydrocarbons of LPG Using Novel MWCNT-Silica Gel Nanocomposite as Packed Column Adsorbent of Gas Chromatography. *Journal of NanoAnalysis*. 2014;1(01):01.
- Seyed Mojtaba Mostafavi MP, Ahmad Rouhollahi, Mohajeri A. Separation of Aromatic and Alcoholic Mixtures using Novel MWCNT-Silica Gel Nanocomposite as an Adsorbent in Gas Chromatography. *Journal of NanoAnalysis*. 2014;1(01):11.
- Parvanian S, Mostafavi SM, Aghashiri M. Multifunctional Nanoparticle Developments in Cancer Diagnosis and Treatment. *Sensing and Bio-Sensing Research*. 2016;1(2):22.
- Mostafavi SM. 3D Graphene Biocatalysts for Development of Enzymatic Biofuel Cells: A Short Review. *Journal of Nanoanalysis*. 2015;2(2):57-62.